

零件名称 PART NAME	Brake Pads Assembly	适用车型 VEHICLE MODEL	CV8QP	零件编号 B/P NO.	HY2401
样品件数 SAMPLE SIZE	4	样品批次 SAMPLE NO	--	样品来源 SUPPLIER	Hongyu
试验依据 TEST SPECIFICATION	Test method from SAE				
试验项目 TEST TIEM	Expansion value and Increment thickness				
试验设备 TEST EQUIPMENTS	High temperature oven and micrometer				
试验方法 TEST METHOD	Test as the requirements of SAEJ160 for the expansion, increment thickness and appearance stability of brake pads.				
顾客要求 CUSTOMER REQUIRE	--				

试验结果:

TEST RESULTS:

Thickness Test item		Thickness of checking area (mm)						Average value (mm)	Expansion value (mm)	Increment (mm)	Con clusi on
		1	2	3	4	5	6				
C V8	Normal temperature	16.028	16.059	16.067	16.028	16.018	16.031	16.039	0.004	-0.027	OK
	High temperature 204℃30min	16.035	16.062	16.069	16.029	16.022	16.037	16.042			
	Cold to normal temperature	15.995	16.065	16.025	16.015	16.009	15.959	16.011			

vite

结论: 合格 CONCLUSION: OK	试验日期: 2012-05-09 DATE:	试验单位: Chongqing Hongyu Friction Products CO., LTD LAB: Products Performance Lab
批准: Wang danying APPROVAL:	审核: Xie qianchuan REVIEW:	试验员: Yang xiaoping TEST PERSONNEL: