

零件名称 PART NAME	Brake Pads Assembly	适用车型 VEHICLE MODEL	CV6QP	零件编号 B/P NO.	HY2209
样品件数 SAMPLE SIZE	4	样品批次 SAMPLE NO	--	样品来源 SUPPLIER	Hongyu
试验依据 TEST SPECIFICATION	Test method from SAE				
试验项目 TEST TIEM	Expansion value and Increment thickness				
试验设备 TEST EQUIPMENTS	High temperature oven and micrometer				
试验方法 TEST METHOD	Test as the requirements of SAEJ160 for the expansion, increment thickness and appearance stability of brake pads.				
顾客要求 CUSTOMER REQUIRE	--				

试验结果:

TEST RESULTS:

Thickness Test item		Thickness of checking area (mm)						Average value (mm)	Expansion value (mm)	Increment (mm)	Conclusion
		1	2	3	4	5	6				
C	Normal temperature	14.575	14.575	14.570	14.598	14.611	14.629	14.593	0.007	-0.005	OK
V	High temperature 204℃30min	14.577	14.585	14.595	14.599	14.625	14.622	14.601			
6	Cold to normal temperature	14.562	14.565	14.572	14.593	14.615	14.619	14.588			

结论: 合格 CONCLUSION: OK	试验日期: 2012-05-09 DATE:	试验单位: Chongqing Hongyu Friction Products CO., LTD LAB: Products Performance Lab
批准: Wang danying APPROVAL:	审核: Xie qianchuan REVIEW:	试验员: Yang Xiaoping TEST PERSONNEL: